

## PERETE EXTERIOR PORTANT - zid 36,5 cm

Crt.	DENUMIRE CARACTERISTICA	UM	PRODUS	
			THERMOKRON 36,5 TK 18-13,8	THERMOKRON 36,5 TK 11,5-13,8
			valoare	valoare
1	Dimensiuni -lungime	mm	180	115
	-latime	mm	<b>365</b>	<b>365</b>
	-inaltime	mm	138	138
2	Masa medie	Kg	10,7	6,7
3	Absorbție apa	%	8-20	8-20
4	Densitate aparenta	Kg/m <sup>3</sup>	1200	1200
5	Volum net	dm <sup>3</sup>	5,9-6,0	3,53-3,64
6	Procent goluri	%	32-34	35,8-37
7	Rezist. la compresiune pe verticala	N/mm <sup>2</sup>	min. 10,0	min. 10,0
8	Rezist. la compresiune pe orizontala	N/mm <sup>2</sup>	min. 2,0	min. 2,0
9	Rezist. la inghet-dezghet	Clasa	F 1	F 1
10	Saruri solubile active (SO)	%	0,17	0,17
11	Permeabilitatea la vapori de apa $\mu$		5/10	5/10
12	Conductivitate termica echiv. $\lambda_{echiv}$	W/m <sup>2</sup> K	0,41	0,36
13	Rezistenta termica R	m <sup>2</sup> K/w	0,89	0,82
14	Reactia la foc (% Euroclasa)	%	1,0 A1	1,0 A1
15	Rezist. medie initiala la forfecare-f <sub>vo</sub>	N/mm <sup>2</sup>	0,38	0,25
16	Nr. buc /m <sup>3</sup> de zidarie tencuita	buc.	93	142

